



An ISO 9001 & 14001 Certified Company

Technical Data Sheet

CEMENTO CRP 305 FLX

Product Description

CEMENTO CRP 305 FLX is a flexible free flowing Re-dispersible polymer powder manufactured by spray drying of special Vinyl Acetate - Ethylene copolymer dispersion. This re-dispersible powder is especially recommended for blending with inorganic binders such as cement, gypsum and hydrated lime based dry mix blends to improve their strength and adhesion properties.

Application

CEMENTO CRP 305 FLX can be used in the manufacturing of-

- Wall putty
- Tile Adhesive
- Tile Grout & Repair Mortars
- Wall & Joint Fillers

Properties

- Very good tensile adhesion strength
- Low temperature workability
- Excellent crack-bridging properties

Processing

- For the manufacturing of dry mix blends, mix CEMENTO CRP 305 FLX with other dry ingredients in an appropriate mixer. Temperature should not be allowed to rise (not more than 40°C) to avoid lumps formation & agglomeration.

Storage

CEMENTO CRP 305 FLX should be stored in a cool, dry place and protect against moisture. Since product is thermoplastic, it should not be kept under pressure or high temperature during storage because of the risk of caking. Storage time should not exceed 6 months from receipt of material.

Blends with hydraulic binders, fillers and pigments show better stability because these components help to prevent caking. However blends of this type should be protected against moisture.

Packaging

25 kg paper bag

Typical Properties

Specification data	Value
Solid content (105 ° C / 2hrs)	98 - 100 %
Bulk density (kg/ m ³)	400 - 600
Moisture Content,%	Max 2.0
Typical general properties	
Visual Appearance	Free Flowing Bright White Powder
Protector colloid / emulsifier system	Polyvinyl alcohol
Particle Size	Max 4% over 400 µm
Whiteness Index	81.3
Tg (Mid Point)	14-18°C
Minimum film forming temperature (MFFT)	5-6°C
Film properties of re-dispersed polymer	Cloudy, tough-elastic

- These figures are only intended as a guide and should not be used in preparing specifications.

Disclaimer:

The suggestion and data in this bulletin are based on information we believe to be reliable. It is offered in good faith, but WITHOUT GUARANTEE, as the conditions and methods of the use of our products are beyond our control. We ALWAYS recommend that the prospective user should determine the suitability of our products and suggestions on an experimental basis first, Before ADAPTING on a commercial scale.

Prepared on 12th May 2019 (Indofil/Indofil Innovative Solutions/Coating/Cemento CRP 305 FLX/May 19/Rev. 0)

Registered Office:

Kalpataru Square, 4th Floor, Kondivita Road, Off Andheri Kurla Road, Andheri (E), Mumbai-400 059. India