

Provisional Literature

## **INDOFIL OIL UR 0715**

**Specialty High Lightfast Fatliquor**

**Indofil Oil UR 0715** is anionic synthetic fatliquor with good softness with good light fastness & heat resistance. It penetrates well and suitable for soft & tight leathers.

### **PHYSICAL PROPERTIES:**

- Composition : Sulphoesters with specialty additives.
- Appearance : Yellow to reddish brown clear viscous liquid.
- pH (1:10) : 7.0 – 9.0
- Stability of Emulsion: Stable to mild acids, hard water & electrolytes.

### **DISCRIPTION:**

**Indofil Oil UR 0715** is anionic lightfast synthetic fatliquor especially designed for all Shoe uppers, softies, garment nappa, gloving and milled leathers. It imparts excellent light fastness & capacity to penetrate & drive all other fatliquors throughout the cross section with light weight.

**Indofil Oil UR 0715** imparts following unique characteristics,

- Anionic penetrative fatliquor.
- Imparts good softness with light weight.
- Imparts silky surface touch & warm handle.
- Lightfast & heat resistant so suitable for white & pastel shades.
- Helps in uniform distribution of retanning agents and fatliquors.
- Compatible with all retannage, vegetable extracts & fatliquors.
- Stable in rechroming

- No bleaching effect

**APPLICATION:**

**Indofil Oil UR 0715** is to be added to the drum by pre dissolving with other fatliquors & water. It is recommended for all types of full grain, corrected grain uppers, suede, nubucks, gloving and milled articles

**Indofil Oil UR 0715** is having wide range of applications as follows,

For Cow/Buff full grain & corrected grain	: 2% – 6% in fatliquoring
For nappa and gloving leathers	: 4% – 10% in fatliquoring
For suede & nubuck leathers	: 3% – 6% in fatliquoring
In Rechroming	: 1% - 4% in Rechroming

**STORAGE STABILITY:** 6-9 months if properly stored in cool & dry place under shed in sealed drums. It is recommended to stir well the product before each & every use.

---

Technical Suggestions are without any obligations

---

Prepared on 18-09-2015

(IIL/SPCD/Leather/Sept 2015/UR 0715/Rev 0)