

#### **Provisional Literature**

# **INDOTAN S2FF**

# **Specialty Resin Syntan**

**INDOTAN S2FF** is anionic, formaldehyde free syntan for fuller & tighter grain, flat surface and buffing properties.

#### PHYSICAL PROPERTIES:

Composition : Syntan based on Synthetic & Organic tanning agent

Appearance : Pale Brown to Brown Powder

Active content :  $96\% \pm 2\%$ 

Ph (10% in water) : 6.0 - 8.0

Stability : Stable to vegetable and mineral tanned leathers.

Solubility : Readily soluble in water

#### **DESCRIPTION:**

**INDOTAN S2FF** produces leathers having exceptionally uniform & fine nap after buffing. Thanks to its mild neutralizing effect which helps in better & deeper penetration of tanning & retanning agents, thus leather has very good filling, less grain loading & fine grain. It is suitable for all type of full grain & corrected grain leathers, shoe uppers, nubucks, suedes, leather goods & upholstery leathers. Its selective filling action promotes level buffing with a tight grain & a more uniform feel & handle.

# **INDOTAN S2FF** imparts following unique properties,

- Low astringent hence good penetration
- > Selective filling in loose areas
- > Smooth flat tight & flexible grain with mellow feel
- > Imparts leveled dyeing & rich shade
- > Gives excellent buffing properties
- > Compatible with all anionic tanning auxiliaries
- ➤ Suitable for free formaldehyde & phenol free leathers



## **APPLICATION:**

**INDOTAN S2FF** is readily soluble in water & is best applied directly to the process vessel as a powder, in the normal manner. It is well suited for the production of full grain & corrected grain Uppers, Softies, Suedes & Nubuck Leathers. Its selective filling action promotes level buffing with a tight grain & a more uniform feel & handle.

**INDOTAN S2FF** also helps to promote level dyeings without affecting the depth of shade & helps to promote even uptake of fatliquors.

•

**INDOTAN S2FF** is having wide range of applications as follows:

Nubuck Leathers : 2 - 4% INDOTAN S2FF

Uppers & Softies : 3 - 4% INDOTAN S2FF

Suede Leathers : 4 - 6% INDOTAN S2FF

Goat Uppers & Linings : 3 - 5% INDOTAN S2FF

Sheep Cabretta : 3 - 5% INDOTAN S2FF

## **STORAGE STABILITY:**

Minimum 9 -12 Months if properly stored in cool & dry place under shed in sealed condition.

Prepared on  $26^{th}$  January 2014 ( ICC/SPCD/Leather/PL/Jan 2014 /Rev. 2)



Technical suggestions are without any obligation