

An ISO 9001 & 14001 Certified Company

Provisional Data Sheet

Rheofil AT 130

Associative Thickener for Paint and Coating system

Rheofil AT 130 is Hydrophobically Modified Alkali Swellable Emulsion.

Rheofil AT 130 has very good compatibility with all the paint ingredients. It is specially processed rheological modifier for thickening latex coating. Formulator can use Rheofil AT 130 with HEC and other types of thickener including PU thickeners.

Rheofil AT 130 is very easy to handle and incorporate into the system. It can be added at different stage as long as paint system is sufficiently alkaline during the incorporation and sufficient mixing is available. It could be incorporated either at mill base stage before or after addition of pigment and extender to give mill base consistency or at the let down stage. Rheofil AT 130 works very efficiently in an alkaline nature so it is recommended that pH of the paint system should be between 9.0 -9.5 before addition of this thickener.

Physical Parameters:

- Appearance : Milky White Emulsion
- Solid Content (150 ° C/ 20 min) : 29.0 - 31.0 %
- pH (As Such) : 2.0-5.0
- Viscosity (Brookfield LVF # 1/60) : <100 cps

Advantages:

- Useful in wide range of water based paint system.
- Provides superior paint application properties like flow ,leveling, and sagging
- Gives better paint quality with stable viscosity
- Does not affect gloss level of paint
- Improves water resistance.
- Easy to handle and incorporate during manufacturing process



An ISO 9001 & 14001 Certified Company

Provisional Data Sheet

Recommended Dosage:

In general 0.2 - 0.75 % of **Rheofil AT 130** calculated on the total quantity of paint system will provide excellent results. The exact dosage will also depend upon the individual paint formulation.

Storage:

Rheofil AT 130 should be stored in tightly closed containers under shade. It should not be exposed to direct sunlight.

Shelf Life:

It can be stored for one year from date of manufacturing as it possesses good storage stability.

Disclaimer:

The suggestion and data in this bulletin are based on information we believe to be reliable. It is offered in good faith, but WITHOUT GUARANTEE, as the conditions and methods of the use of our products are beyond our control. We ALWAYS recommend that the prospective user should determine the suitability of our products and suggestions on an experimental basis first, Before ADAPTING on a commercial scale.

Prepared on 25 th June 2013 (Indofil/SPCD/Coating/June 2013/Rev. 0)

Registered Office:

**Kalpataru Square, 4th Floor, Kondivita Road, Off Andheri Kurla Road, Andheri (E), Mumbai-400 059.
India**